



Wire Mesh

Ref. No	Cross-sectional Area(mm/m ²)		Wire Diameter(mm)		Wire Spacing(mm)		Nominal Mass (KG/m ²)
	Main	Cross	Main	Cross	Main	Cross	
Square Fabric							
A13	664	664	13	13	200	200	10.42
A12	565	565	12	12	200	200	8.88
A11	475	475	11	11	200	200	7.46
A10	393	393	10	10	200	200	6.16
A9	318	318	9	9	200	200	4.99
A8	252	252	8	8	200	200	3.95
A7	193	193	7	7	200	200	3.02
A6	142	142	6	6	200	200	2.22
A5	98	98	5	5	200	200	1.54
A4*	63	63	4	4	200	200	0.99
Rectangular Fabric							
B13	1328	252	13	8	100	200	12.40
B12	1131	252	12	8	100	200	10.86
B11	950	252	11	8	100	200	9.44
B10	785	252	10	8	100	200	8.14
B9	636	252	9	8	100	200	6.97
B8	503	252	8	8	100	200	5.93
B7	385	193	7	7	100	200	4.53
B6	283	193	6	7	100	200	3.73
B5	196	193	5	7	100	200	3.05
Long Fabric							
C13	1328	126	13	8	100	400	11.41
C12	1131	126	12	8	100	400	9.87
C11	950	126	11	8	100	400	8.44
C10	785	71	10	6	100	400	6.72
C9	636	71	9	6	100	400	5.55
C8	503	49	8	5	100	400	4.34
C7	385	49	7	5	100	400	3.41
C6	283	49	6	5	100	400	2.61
C5	196	49	5	5	100	400	1.93
Small Square Fabric							
D13	1328	1328	13	13	100	100	20.85
D12	1131	1131	12	12	100	100	17.76
D11	950	950	11	11	100	100	14.92
D10	785	785	10	10	100	100	12.32
D9	636	636	9	9	100	100	9.98
D8	503	503	8	8	100	100	7.90
D7	385	385	7	7	100	100	6.04
D6	283	283	6	6	100	100	4.44
D5	196	196	5	5	100	100	3.08
D4*	126	126	4	4	100	100	1.97

